

TE-W250

WOVEN GEOTEXTILE



TE-W250 is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. TE-W250 resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	MARV VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	250 (1113)
Grab Elongation	ASTM D 4632	%	12
Trapezoidal Tear	ASTM D 4533	lbs (N)	90 (400)
CBR Puncture Resistance	ASTM D 6241	lbs (N)	750 (3338)
Permittivity*	ASTM D 4491	l/sec	0.05
Water Flow*	ASTM D 4491	gpm/ft ² (l/min/m ²)	4 (163)
Apparent Opening Size (AOS)	ASTM D 4751	U.S. Sieve (mm)	40 (.425)
U.V. Resistance	ASTM D 4355	%/hrs	70/500
TYPICAL ROLL DIMENSIONS			
Roll Dimensions		ft	12.5 x 360 15 x 300 17.5 x 258
Roll Area		yd ²	500
Estimated Roll Weight		lbs	310

NOTES:

*At time of manufacturing. Handling, storage, and shipping may change these properties.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL CONTAINMENT

Toll Free: 1-866-327-1957 | Email: info@titanenviro.com | Web: www.titanenviro.com

(Rev. April, 2018)

TRUST. QUALITY. VALUE